

COVALENCE[®] HTLP60-DCS 2 LAYERS

Product Information

Product description: Covalence[®] HTLP60-DCS system is a wrap-around heat-shrinkable sleeve field-joint coating system for pipeline operating at ambient and elevated temperatures.

Construction: Two-layer system

- *First layer:* High shear strength copolymer adhesive.
- *Second layer:* Radiation cross-linked, high density polyethylene with permanent Change Indicator (PCI).

The HTLP60-DCS is compatible with most commonly used steel pipe coatings and is used for offshore and onshore girth weld protection or to recoat (rehabilitate) long pipe sections and large radius bends. The installation is carried out directly on the cleaned and pre-heated pipe surface without any primer required. During installation, heat-shrinkable sleeve is wrapped around the joint. Heat is then applied to the sleeve which shrinks to form a tight fit around the joint. The cross-linked outer layer forms a tough barrier against mechanical damage and moisture transmission.

Note HTLP60-DCS can also be applied with liquid epoxy primer as 3-layer coating. See PDS HTLP60-DCS for more info.

Features:

- Fully resistant to shear forces induced by soil and thermal movements.
- Sleeve allows fast installation and formation of strong mechanical & chemical bonds.
- Superior cathodic disbondment and hot water immersion resistance.
- No special equipment (standard gas torch & a roller).
- Dimpled backing provides a "permanent change" indicator for application of heat.

Benefits:

- The HTLP is tough & lasts as long as a 3-layer, factory applied coating.
- Allows fast application combined with high performance.
- No primer required. Makes installation fast and easy. Keeps installation costs low.
- Offers the optimum barrier protection against corrosion.
- Dimpled backing allows easy post-heat inspection and offers a reliable inspectability at any time.

Product selection guide

Max operating temperature	65°C.
Compatible line coatings	PE, PP
Min. preheat temperature	80°C
Recommended pipe preparation	Sa 2½ or ST3
Soil stress restrictions	None
Performance	EN 12068 C50 UV

Product properties

Backing

Property	Test method	Typical value
Tensile strength at break	ASTM D-638	3300 psi (22.8 MPa)
Elongation at break	ASTM D-638	600 %
Hardness, Shore D	ASTM D-2240	57
Density	ASTM D-792	0.97 kg/dm ³
Shrink force	ASTM D-638, @ 150°C	40 psi
Dielectric Strength	ASTM D-149	900 volts/mil (35 kV/mm)
Moisture absorption	ASTM D-570	0.04%

Adhesive

Property	Test method	Typical value
Softening Point	ASTM E-28	110°C
Lap shear	EN12068 @ 50°C @ 60°C	0.06 N/mm ² 0.05 N/mm ²

Installed sleeve

Property	Test method	Typical value
Peel to Steel	EN12068 @ 10 mm/min DIN30672 @ 100 mm/min	2 N/mm 7 N/mm
Cathodic disbondment	EN12068 / ISO21809-3 @ 50°C, 28 days	13 mm radius
Hot water immersion	ISO21809-3 @ 50°C, 100 days 60°C, 100 days	P100/P0 ≥ 0.75 P100/P0 ≥ 0.75
Impact resistance	EN12068 class C	> 15 J
Indentation resistance	EN12068, Class C, @ 50°C ISO21809-3, 14A1 @ 60°C	Residual thickness > 0.6 mm > 0.6 mm

Note: The typical values in this data sheet are based on lab prepared samples. Values shown are not to be interpreted as product specifications. All properties are at 23°C unless otherwise specified.

Product thickness

	/E	/C	/F
Backing as supplied	0.9 mm (0.035 in)	1.04 mm (0.041 in)	1.04 mm (0.041 in)
Backing fully free recovered	1.2 mm (0.047 in)	1.4 mm (0.055 in)	1.4 mm (0.055 in)
Adhesive as supplied	1.3 mm (0.051 in)	1.5 mm (0.060 in)	1.8 mm (0.071 in)

* Other thickness available on request. Minimum order quantities apply.

Product order information

- Covalence® HTLP60-DCS products are available
- As cut piece (pre-cut, no cut corners, with separate closure patch)
 - As Uni-sleeve (pre-cut, with cut corners, with attached closure patch)
 - As a roll (closure patches to be ordered separately)

Select sleeve width that will overlap onto the mill-applied coating by 50 mm (2 inches) minimum on each side of the weld joint. Take a 10% shrinkage during installation of sleeve into account when calculating minimum sleeve width.

Cut piece / Uni-sleeve

Example	HTLP60-DCS-DN200-450/E(/UNI)	
	Designation	Standard ordering options
DN200	Outside pipe diameter	DN50 – DN1500 (2.375" – 60.000")
450	Sleeve width (mm)	450 mm (17.75") 500 mm (19.75")
/E	Product thickness	/E /C /F
UNI	Designates pre-attached closure patch	Optional

Roll form (closure patch to be ordered separately)

Example	HTLP60-DCS-450X30M/C-RL	
	Designation	Standard ordering options
450	Sleeve width (mm)	450 mm (17.75") 500 mm (19.75")
30M	Roll length	30M (100ft)
/C	Product thickness	/E /C /F

Rolls can have a splice. Max 10% of the roll order will have a splice. Min partial length will be 5M or 15 ft.

Closure patches (to be ordered separately)

Example	WPCP-IV-4x17(S50)	
	Designation	Standard ordering options
4	Patch width (in.)	4 (100 mm) 6 (150 mm) 8 (200 mm)
17	Patch length (in.)	17: 450 mm (17.75") 20S: 500 mm (19.75")
(S50)	Packaging quantity in plastic bag.	50 pc

General information

Product dimension	Sleeve cut lengths and appropriate closure patch widths depend on the pipe size and product construction, see latest application table AT-GIRTHWELD.
Installation guide	For proper product installation, see latest application guideline.
Handling	Handle with care. Keep boxes upright.
Storage	Store indoor, clean and dry, away from direct sunlight in a cool place below +50°C. Unlimited shelf life.
Documentation	Extensive information is available on our website. Application instructions and other documentation can be obtained by contacting our head office, from our local distributor or by sending email to info@sealforlife.com
Certified staff	Application of the described coating system shall be carried out by certified personnel.



Seal For Life Industries - Stopaq B.V.
Stadskanaal, the Netherlands
Tel: +31 599 696 170

Seal For Life Industries BV
Westerlo, Belgium
Tel: +32 14 722 500

Seal For Life Industries US LLC
San Diego, USA
Tel: +1 858 633 9785

Seal For Life Industries Mexico
S de R.L. de C.V.
Tijuana, Mexico
US Tel: +1 858 633 9785
MX Tel: +52 664 647 4300

Seal For Life India Private Ltd.
Baroda, India
Tel: +91 2667 264 721

Further information is available on our website www.sealforlife.com, or by sending an inquiry to info@sealforlife.com

DISCLAIMER: Seal For Life Industries warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the technical data sheet when used in compliance with Seal For Life Industries' written instructions. Because many installation factors are beyond the control of Seal For Life Industries, the user shall determine the suitability of the products for the intended uses and assume all risks and liabilities in connection herewith. Seal For Life's liability is stated in its General Terms and Conditions of Sale. Seal For Life Industries makes no other warranty either express or implied. All information contained in this document is to be used as a guide and is subject to change without notice. This technical data sheet supersedes all previous data sheets on this product.