PRODUCT DATA SHEET

POLYKEN® 1027-ISO

Product Information

Product description: Polyken® liquid adhesive systems are recommended for use with only Polyken® coating systems. The liquid adhesive systems consist of butyl based elastomers blended with polymeric resins dissolved in an organic solvent system. They can be used for hand brush applications and conform to local national standards.

The Polyken 1027-ISO Liquid adhesive system is ideal for hand brush application to rough, reconditioned, or grit-blasted pipe surfaces. It provides a uniformly smooth, instant tack surface for Polyken® coating systems.

Caution:

- Store away from heat source. Read all label instructions prior to use.
- Properly stored, all Polyken[®] liquid coating systems have a shelf life of 3 years. Please request an application specification and storage guideline from Seal For Life.
- Polyken[®] liquid adhesive systems are FLAMMABLE MIXTURES.

| Product selection guide | |
|------------------------------|---|
| Max. operating temperature | 85°C (185°F) |
| Additional mechanical layer | Subsequent Polyken coating systems |
| Compatible line coatings | Carbon steel, PE, FBE, PP,CTE, Tape, |
| Recommended pipe preparation | SSA-ST2 (SSPC-SP3) or SSA-SA 2 (SSPC-SP6) 1 – 3 mil anchor profile (25 – 76 micron anchor profile) |
| Performance | AWWA, DIN, EN, ISO standards |

| Ordering information | |
|----------------------|------------------------------|
| Item number | Description |
| 583851-000 | 1027-ISO LIQUID ADH 1L (C12) |
| 115335-000 | 1027-ISO LIQUID ADH 10L |
| 14210-000 | 1027-ISO LIQUID ADH 200L |

For other ordering options please contact your Seal For Life representative.

| Product properties of Polyken® 1027-ISO | | |
|---|-----------------------------|--|
| | Typical values | |
| Property | Units | |
| Description | # 1027-ISO | |
| Base | Rubber/Resins | |
| Solvent | See Safety Data Sheet (SDS) | |
| Total Solids | 30 % | |
| Weight/Liter | 0.81 kg | |
| Viscosity | Medium Syrup | |
| Flash Point | < 23°C | |
| Color | Black | |
| VOC | 0.59 kg/l | |
| Shelf life | 3 years | |
| Coverage rate | 7.4 m²/liter | |
| (estimated/varies) | | |

| Application instruction: Job preparation | |
|--|--|
| Tools, equipment and auxiliaries | Temperature gauge, DFT/WFT gauge Primer application equipment/agitator, |
| Additional coating materials | Subsequent Polyken coating systems, 933-25, 931, 939 |
| High humidity | Polyken® 1027-ISO can be applied in a humid atmosphere. The substrate should be free from condensing water which can be reached by keeping the temperature at least 5°F (3°C) above dew point. |
| Work area and substrate | The substrate surface should be dry, clean and protected against negative weather influences. |
| Product conditions | The Polyken® 1027-ISO shall be stored and/or transported in a dry, ventilated location. Storage temperature shall be a minimum of 60°F (16°C) and a maximum of 125°F (52°C). The minimum primer temperature for application will be 60°F (16°C). |

| Application instru | uction: Surface preparation |
|----------------------------------|---|
| General | The area to be coated has to be clean, dry, and free from oil, grease and dust. All contamination including mill-scale has to be removed. |
| Degreasing | Degrease surfaces with Toluene or Heptane and e.g. a lint-free cloth. |
| Preventing condensation of water | Prior to and during the application, the temperature of the substrate(s) must be at least 5°F (3°C) above the dew point. |
| Substrate temperature | Temperature of the substrate should preferably be between +68°F and +104°F (+20°C / +40°C). Preheating may be required. |

| Application in | struction: Brief version |
|----------------|---|
| Step 1 | Clean substrate to SSA-ST2, SSPC-SP3 (power wire brush) or SSA-SA 2, SSPC-SP6 (commercial blast). Surface (anchor) profile depth shall be no less than 1.0 mils (25 micron) and no greater than 3 mils (76 micron). |
| Step 2 | Uniform primer application achieving 2 to 3 mil WFT. Primer should be "dry to touch" before application of inner layer. |

^{*} For further detailed information, please view the corresponding Application Guideline *

| I | Handling and commissioning | |
|---|----------------------------|--|
| | Exposure to loads | Objects coated with Polyken® 1027-ISO should not be exposed to loads e.g. from supports- or lifting equipment. |
| | Backfill | Backfill is possible immediately after completion of the coating application and after the subsequent Polyken coating system has been applied. Consult application guidelines for specific instructions. Backfill should be clean and not contain any foreign items that can cause damage to the coating system. |

| Information | |
|-----------------|--|
| Documentation | Extensive information is available on our web- site. Application instructions and other documentation can be obtained by contacting our offices, from our local distributor or by sending an email to info@sealforlife.com |
| Certified staff | Application of the described coating system shall be carried out by certified personnel. |



DISCLAIMER: Seal For Life Industries warrants that the product conforms to its chemical and physical SEALFORLIFE

In dust ries warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the technical data sheet when used in compliance with Seal For Life Industries' written instructions. Because many installation factors are beyond the control of Seal For Life Industries, the user shall determine the suitability of the products for the intended uses and assume all risks and liabilities in connection herewith. Seal for Life's liability is stated in its General Terms. and Conditions of Sale. Seal For Life Industries makes no other warranty either express or implied. All information contained in this technical data sheet is to be used as a guide and is subject to change without www.sealforlife.com notice. This technical data sheet supersedes all previous data sheets on this product. Seal For Life Industries is a registered marks of the Berry Global Group, Inc. or its affiliates.

Local distributor / representative

For contact details of local distributor / representative Please visit www.sealforlife.com

Franklin, MA, USA Tel: +1 508 918 1600 US Toll Free: +1 800 248 7659 Fax:+1 812 250 0834 franklin@sealforlife.com

Seal For Life Industries LLC Seal For Life Industries Mexico S de R.L. de C.V. Tijuana, Mexico

Tel USA +1 858 633 9797 Fax US: +1 858 633 9740 Tel Mexico: +52 664 647 4397 Fax Mexico: +52 664 607 9105 mexico@sealforlife.com

Seal For Life Industries Stopaq B.V. Stadskanaal, the Netherlands Tel: +31 599 696 170 Fax: +31 599 696 177 info@sealforlife.com

Seal For Life Industries BVBA Westerlo, Belgium Tel: +32 14 722 500 Fax: +32 14 722 570 belgium@sealforlife.com

Seal For Life India Private Ltd. Baroda, India

Tel: +91 2667 264 721 Fax: +91 2667 264 724 india@sealforlife.com