

## POLYKEN® 934

### Product Information

**Product description:** The Polyken® 934 is a cold applied tape coating system designed as repair system for all types of main line coatings and specialty piping. The unique high tack adhesive retains conformability over a wide temperature range. Coupled with a very malleable polyethylene backing, this versatile tape system can be applied by hand or with a wrapping machine.

#### Features:

- Heavy duty adhesive.
- Conformable to irregular shapes.
- Worldwide reference lists.
- Complies with AWWA standard C-209, EN12068, DIN30672.
- Compatible with generic plant coatings systems.

#### Benefits:

- Ensures a strong bond & impervious seal.
- Offers a solution for nearly every application.
- Makes installation fast and easy.
- Established in-ground history.
- Reliable, high performance corrosion protection.
- Versatile.

### Product selection guide

Max. operating temperature	66°C (150°F)
Recommended primer	1027 or 1033A
Additional mechanical layer	955 or 954
Compatible line coatings	PE, PP, FBE, Cold Tape, CT, CTE
Recommended pipe preparation	SSA-ST2 (SSPC-SP3) or SSA-SA 2 (SSPC-SP6) 1 – 3 mil anchor profile (25 – 76 micron anchor profile)
Performance	AWWA C209, EN12068, DIN30672
Shelf life	5 years

### Product construction

	934-35	934-50
Backing	7 mils (0.178 mm)	10 mils (0.254 mm)
Adhesive	28 mils (0.711 mm)	40 mils (1.016 mm)
Backing color	White	White

### Product properties

Property	Method	Typical values		Units
		934-35	934-50	
Tensile strength	ASTM D 1000	15	25	pli
		2.6	4.4	N/mm
Elongation	ASTM D 1000	150	150	%
Peel adhesion to primed steel	ASTM D 1000	9.3	19.9	pli
		1.6	3.5	N/mm
Cathodic disbondment	ASTM G 8	0.25	0.38	in radius
		6.4	9.7	mm
Water vapor transmission	ASTM E 96B	0.07	0.07	perm
Water vapor transmission rate	ASTM F 1249 (100°F, 100% RH)	0.04	0.04	g/100 in <sup>2</sup> /24 hr
		0.6	0.8	g/m <sup>2</sup> /24 hr
Volume resistivity	ASTM E 257	4 X 10 <sup>14</sup>	4 X 10 <sup>14</sup>	Ω.cm
Dielectric breakdown	ASTM D 1000	650	600	V/mil
		25.6	23.6	kV/mm
Dielectric strength	ASTM D 149	21	30	kV
Insulation resistance	ASTM D 1000	1.4 x 10 <sup>7</sup>	2.0 x 10 <sup>7</sup>	MΩ

### Equation for Pipe Coating Requirements

**Squares\*\* of coating required**  $\frac{(\text{width of coating in inches}) \times (\text{area of pipe in square feet})}{(\text{width of coating in inches} - \text{overlap in inches}) \times 100}$

\* Area of pipe in ft<sup>2</sup> = (diameter in inches / 12) x 3.1416 x length in feet  
 \*\* One Square = one hundred square feet = 9.29 square meters

**Square meters of coating required**  $\frac{(\text{width of coating in mm}) \times (\text{area of pipe in square meter})}{(\text{width of coating in mm} - \text{overlap in mm})}$

\* Area of pipe in m<sup>2</sup> = (diameter in mm / 1000) x 3.1416 x length in meter

**Squares\*\* per roll**  $\frac{(\text{width of roll in inches}) \times (\text{length of roll in feet})}{(12) \times (100)}$

**Square meters per roll**  $\frac{(\text{width of roll in mm}) \times (\text{length of roll in m})}{(1000)}$

**Rolls Required**  $\frac{(\text{squares of coating required})}{(\text{squares per roll})}$

**Rolls Required**  $\frac{(\text{square meters of coating required})}{(\text{square meters per roll})}$

### Ordering information

Polyken® 934 Tape Coatings are available in roll form.

Example **934-35 WHI 2X50 ft 4.1cm**

934	Product type	Standard Ordering options
35	Total tape thickness in mils	35 mils (0.89 mm)
		50 mils (1.27 mm)
WHI	Tape backing color	White (WHI)
2	Tape width in inches	2" (50 mm), 4" (101 mm), 6" (152 mm)
50	Tape roll length in feet	50 ft (15 m)
4.1	Tape inner core diameter	4.1 cm (1.6"), 7.6 cm (3.0")

For other ordering options please contact your Seal For Life representative.

Application instruction: Job preparation	
<b>Tools, equipment and auxiliaries</b>	Temperature gauge, DFT/WFT gauge, Primer application equipment/agitator, Tape application equipment, Coating "hot box"
<b>Additional coating materials</b>	931 or 939 filler material, and 954, or 955 mechanical protection layers
<b>High humidity</b>	Polyken® 934 can be applied in a humid atmosphere. The substrate should be free from condensing water which can be reached by keeping the temperature at least 5°F (3°C) above dew point.
<b>Work area and substrate</b>	The substrate surface should be dry, clean and protected against negative weather influences.
<b>Product conditions</b>	The Polyken® 934 shall be stored and/or transported in a dry, ventilated location. Storage temperature shall be a minimum of 60°F (16°C) and a maximum of 120°F (49°C). The minimum primer and roll body temperature for application will be 60°F (16°C).

Application instruction: Surface preparation	
<b>General</b>	The area to be coated has to be clean, dry, and free from oil, grease and dust. All contamination including mill-scale has to be removed.
<b>Degreasing</b>	Degrease surfaces with Toluene or Heptane and e.g. a lint-free cloth.
<b>Preventing condensation of water</b>	Prior to and during the application, the temperature of the substrate(s) must be at least 5°F (3°C) above the dew point.
<b>Substrate temperature</b>	Temperature of the substrate should preferably be between 68°F and 104°F (20°C / 40°C). Preheating may be required.

Application instruction: Brief version	
<b>Step 1</b>	Clean substrate to SSA-ST2, SSPC-SP3 (power wire brush) or SSA-SA 2, SSPC-SP6 (commercial blast). Surface (anchor) profile depth shall be no less than 1.0 mils (25 micron) and no greater than 3 mils (76 micron).
<b>Step 2</b>	Uniform primer application achieving 2 to 3 mil WFT. Primer should be "dry to touch" before application of inner layer.
<b>Step 3</b>	If required, apply filler material onto weld seam.

\* For further detailed information, please view the corresponding Application Guideline \*

<b>Step 4</b>	Spirally or circumferentially apply the 934 with a 1% to 2% neckdown. A minimum of two layers of the 934 shall be applied.
<b>Step 5</b>	If a single 934 layer is required, then a mechanical protection outerwrap layer (905, 954, 955) shall be applied over the single layer of 934.
<b>Step 6</b>	Perform holiday detection per NACE SP0274

Handling and commissioning	
<b>Exposure to loads</b>	Objects coated with Polyken® 934 should not be exposed to loads e.g. from supports- or lifting equipment.
<b>Backfill</b>	Backfill is possible immediately after completion of the coating application. Consult application guidelines for specific instructions. Backfill should be clean and not contain any foreign items that can cause damage to the coating system.

Information	
<b>Documentation</b>	Extensive information is available on our web-site. Application instructions and other documentation can be obtained by contacting our offices, from our local distributor or by sending an email to <a href="mailto:info@sealforlife.com">info@sealforlife.com</a>
<b>Certified staff</b>	Application of the described coating system should be carried out by certified personnel.



Seal For Life Industries Mexico S de R.L. de C.V.  
Tijuana, Mexico  
USA Tel: +1 858 633 9797  
Mx Tel: +52 664 647 4397  
mexico@sealforlife.com

Seal For Life Industries - Stopaq B.V.  
Stadskanaal, the Netherlands  
Tel: +31 599 696 170  
Fax: +31 599 696 177  
info@sealforlife.com

Seal For Life Industries BVBA  
Westerlo, Belgium  
Tel: +32 14 722 500  
Fax: +32 14 722 570  
belgium@sealforlife.com

Seal For Life India Private Limited  
Baroda, India  
Tel: +91 2667 264 721  
Fax: +91 2667 264 724  
india@sealforlife.com

DISCLAIMER: Seal For Life Industries warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the technical data sheet when used in compliance with Seal For Life Industries' written instructions. Be many installation factors are beyond the control of Seal For Life Industries, the user shall determine the suitability of the products for the intended uses and assume all risks and liabilities in connection herewith. Seal For Life's liability is stated in its General and Conditions of Sale. Seal For Life Industries makes no other warranty either express or implied. All information contained in this document is to be used as a guide and is subject to change without notice. This technical data sheet supersedes all previous sheets on this product.