

POLYKEN® YGIII

Product Information

Product description: The Polyken® YGIII System is a multilayer coating system used primarily for the protection of steel and ductile iron water pipelines. The multilayer coating system consists of:

- 1) A liquid adhesive to be applied to the pipe surface
- 2) An anti-corrosion tape to be applied over the adhesive
- 3) A mechanical protective tape or tape system to be applied over the anti-corrosion tape

Polyken® 1019, low VOC Polyken® 1033A and Zero VOC Polyken® 1039 liquid adhesives provide a uniformly smooth contact surface to promote high adhesion of the coating system to the pipe. Liquid Adhesives are formulated with corrosion inhibitors and adhesion promoters. The unique formulation flows and fills surface profiles and irregularities. The adhesives in these and all Polyken® tape systems contain proven anti-microbial additives.

The Anti-Corrosion layer Polyken® 989 is engineered to assure a high bond to the primed surface with excellent conformability characteristics.

The Middle and Outer mechanical protection layers Polyken® 955 and 956 achieve a complete bond to the 989 inner layer, providing maximum handling and in-service protection for the coating system.

Features:

- Worldwide reference lists.
- Impermeable to oxygen and moisture.
- Resistant to soil stress.
- Zero VOC coating system available.
- Uniform coating thickness.
- Low cathodic protection-current requirements.
- Exceeds AWWA standards.
- Compatible with large pipe diameters.

Benefits:

- Proven long-term performance.
- Low cathodic protection costs. Saving cost over the life of the pipeline.
- Superior in-ground performance.
- Environmentally friendly.
- Easy to apply.
- Saving cost over the life of the pipeline.
- Reliable, high performance corrosion protection.
- Minimizes inventory, thus saving money.

Product selection guide

Max. operating temperature	85°C (185°F)
Recommended primer	1019, 1033A or 1039
Recommended pipe preparation	SSA-SA 2 (SSPC-SP6) 1 – 3 mil anchor profile (25 – 76 micron anchor profile)
Performance	AWWA C-214

Product construction

	Inner Layer 989-20	Middle Layer 955-30	Outer Layer 952/956-30
Backing	9 mils (0.229 mm)	25 mils (0.635 mm)	25 mils (0.635 mm)
Adhesive	11 mils (0.279 mm)	5 mils (0.127 mm)	5 mils (0.127 mm)
Backing color	Black	Gray	White, Blue

Product properties of Polyken® YGIII

Property	Method	Typical values		Units
		989-20	955-30 & 956-30	
Tensile strength	ASTM D1000	30 5.3	50-65 8.8-11.4	pli N/mm
Elongation	ASTM D1000	300	300-400	%
System properties 80 mils system: 989-20 + 955-30 + 956-30				
Peel adhesion to primed steel	ASTM D1000	18.7 3.3		pli N/mm
Cathodic disbondment	ASTM G8	0.25 6.4		in radius mm radius
Water vapor transmission	ASTM E96B	0.07		perm
Water vapor transmission rate	ASTM F1249 (100°F, 100%RH)	0.03		g/100in ² /24 hr g/m ² /24hr
Volume resistivity	ASTM E257	10 ¹⁵		Ω.cm
Dielectric breakdown	ASTM D1000	650 25.6		V/mil kV/mm
Dielectric strength	ASTM D149	20-23		kV
Impact resistance	ASTM G-14	90 10		in-lb J
Impact resistance	ASTM G-13	1000 4450		lb N
Penetration resistance	ASTM G-17	11-15		%

Equation for Pipe Coating Requirements

Squares of coating required** $\frac{(\text{width of coating in inches}) \times (\text{area of pipe in square feet})}{(\text{width of coating in inches} - \text{overlap in inches}) \times 100}$

* Area of pipe in ft² = (diameter in inches / 12) x 3.1416 x length in feet

** One Square = one hundred square feet = 9.29 square meters

Square meters of coating required $\frac{(\text{width of coating in mm}) \times (\text{area of pipe in square meter})}{(\text{width of coating in mm} - \text{overlap in mm}) \times 100}$

* Area of pipe in m² = (diameter in mm / 1000) x 3.1416 x length in meter

Squares per roll** $\frac{(\text{width of roll in inches}) \times (\text{length of roll in feet})}{(12) \times (100)}$

Square meters per roll $\frac{(\text{width of roll in mm}) \times (\text{length of roll in m})}{(304.8) \times (30.48)}$

Rolls Required $\frac{(\text{squares of coating required})}{(\text{squares per roll})}$

Rolls Required $\frac{(\text{square meters of coating required})}{(\text{square meters per roll})}$

Ordering information

Polyken® 989, 955 and 956 Tape Coatings are available in roll form.

Example **989-20 BLK 12X1000**

989	Product type	Standard Ordering options
20	Total tape thickness in mils	20 mils (0.51 mm)
BLK	Tape backing color	Black (BLK)
12	Tape width in inches	4" (101mm), 6" (152 mm), 9" (228 mm), 12" (305 mm), 18" (457 mm)
1000	Tape roll length in feet	800 ft (244 m), 1000 ft (305 m)
951/955-30 GRA 12X1000		
955	Product type	Standard Ordering options
30	Total tape thickness in mils	30 mils (0.762 mm)
GRA	Tape backing color	Gray (GRA)
12	Tape width in inches	4" (101 mm), 6" (152 mm), 9" (228 mm), 12" (305 mm), 18" (457 mm)
1000	Tape roll length in feet	800 ft (244 m), 1000 ft (305 m)
952/956-30 WHI UVI 12X1000		
956	Product type	Standard Ordering options
30	Total tape thickness in mils	30 mils (0.762 mm)
WHI	Tape backing color	White (WHI), Blue (BLU)
12	Tape width in inches	4" (101 mm), 6" (152 mm), 9" (228 mm), 12" (305 mm), 18" (457 mm)
1000	Tape roll length in feet	800 ft (244 m), 1000 ft (305 m)
UVI	Designates Ultraviolet Protection	Standard

For other ordering options please contact your Seal For Life representative.

Application instruction: Job preparation	
Tools, equipment and auxiliaries	Temperature gauge, DFT/WFT gauge, Primer application equipment/agitator, Tape application equipment, Coating "hot box"
Additional coating materials	933-25 weld seam coating,
High humidity	Polyken® YGIII can be applied in a humid atmosphere. The substrate should be free from condensing water which can be reached by keeping the temperature at least 5°F (3°C) above dew point.
Work area and substrate	The substrate surface should be dry, clean and protected against negative weather influences.
Product conditions	<p>The Polyken® YGIII shall be stored and/or transported in a dry, ventilated location. Storage temperature shall be a minimum of 60°F (16°C) and a maximum of 120°F (49°C). The minimum primer temperature for application will be 60°F (16°C).</p> <p>The YGIII anti-corrosion layer shall be applied and maintained at a minimum roll body temperature of 70°F (21°C) maximum of 90°F (32°C) and the mechanical protection layer applied and maintained at a minimum roll body temperature of 90°F (32°C), Maximum of 120°F (49°C).</p> <p>The YGIII coating system rolls shall be stored in a temperature controlled storage room for a minimum of 24 hours prior to application. The ambient storage temperature shall not exceed 120° F (49°C).</p>

Step 4	Spirally apply the inner layer (anti corrosion) with a 1% to 2% neckdown and no less than a 1" overlap
Step 5	Spirally apply the middle layer (mechanical Protection) with a 1% to 2% neckdown and no less than a 1" overlap.
Step 6	Spirally apply the outer layer (mechanical Protection) with a 1% to 2% neckdown and no less than a 1" overlap.
Step 7	Perform holiday detection per NACE RP-02-74

Handling and commissioning	
Exposure to loads	Objects coated with Polyken® YGIII should not be exposed to loads e.g. from supports- or lifting equipment.
Backfill	Backfill is possible immediately after completion of the coating application. Consult application guidelines for specific instructions. Backfill should be clean and not contain any foreign items that can cause damage to the coating system.

Information	
Documentation	Extensive information is available on our website. Application instructions and other documentation can be obtained by contacting our offices, from our local distributor or by sending an email to info@sealforlife.com
Certified staff	Application of the described coating system should be carried out by certified personnel.

Application instruction: Surface preparation	
General	The area to be coated has to be clean, dry, and free from oil, grease and dust. All contamination including mill-scale has to be removed.
Degreasing	Degrease surfaces with Toluene or Heptane and e.g. a lint-free cloth.
Preventing condensation of water	Prior to and during the application, the temperature of the substrate(s) must be at least 5°F (3°C) above the dew point.
Substrate temperature	Temperature of the substrate should preferably be between 68°F and 104°F (20°C / 40°C). Preheating may be required.

Application instruction: Brief version	
Step 1	Clean substrate to SSPC-SP6 /NACE3 or SA 2 (commercial blast) with a 1 – 3 mil anchor profile (25 – 76 micron anchor profile)
Step 2	Uniform primer application achieving 2 to 3 mil WFT. Primer should be "dry to touch" before application of inner layer.
Step 3	If required, apply weld seam coating

* For further detailed information, please view the corresponding Application Guideline *



Seal For Life Industries LLC
Franklin, KY, USA
Tel: +1 508 918 1714
Toll Free: +1 800 248 7659
Fax: +1 508 918 1910
info@sealforlife.com

Seal For Life Industries
Tijuana, Mexico
Tel USA: +1 858 633 9797
Fax USA: +1 858 633 9740
Tel Mx: +52 664 647 4397
Fax Mx: +52 664 607 9105
mexico@sealforlife.com

Seal For Life Industries BV
Stadskanaal, The Netherlands
Tel: +31 599 696 170
Fax: +31 599 696 177
info@sealforlife.com

Seal For Life Industries BVBA
Westerlo, Belgium
Tel: +32 14 722 500
Fax: +32 14 722 570
belgium@sealforlife.com

Seal For Life Private Ltd.
Baroda, India
Tel: +91 2667 264 721
Fax: +91 2667 264 724
india@sealforlife.com

Anodeflex® - Stopaq® - Polyken® - Covalence® - Powercrete® - Sealtaq® - Blockr®

DISCLAIMER: Seal For Life Industries warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Seal For Life Industries written instructions. Since many installation factors are beyond the control of Seal For Life Industries, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Seal For Life Industries liability is stated in the standard terms and conditions of sale. Seal For Life Industries makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date on the left. Polyken® is a registered trademark of Seal For Life Industries.